







































측정위치	A1				
X (전달시간, μs)	25.7	52.6	78.9	104.6	127.6
Y (측정거리, cm)	10	20	30	40	50
추세선식	$Y = 3.906X - 0.42$				
상관계수 (r^2)	0.9992				
전달속도 V_i (Km/s)	3.906				
$V_d = 1.05V_i$	4.101				
품 질 평 가	양호				




초음파법에 의한 콘크리트 압축강도(Mpa)	
f_{ck} (일본건축학회식)	25.6
f_{ck} (일본재료학회식)	29.5

측정위치	A2				
X (전달시간, μs)	26.8	52.1	75.3	101.9	126.7
Y (측정거리, cm)	10	20	30	40	50
추세선식	$Y = 4.005X - 0.663$				
상관계수 (r^2)	0.9997				
전달속도 V_i (Km/s)	4.005				
$V_d = 1.05V_i$	4.205				
품 질 평 가	양호				




초음파법에 의한 콘크리트 압축강도(Mpa)	
f_{ck} (일본건축학회식)	27.8
f_{ck} (일본재료학회식)	30.6

측정위치	P1-기둥				
X (전달시간, μs)	25.7	52.6	78.9	104.6	127.6
Y (측정거리, cm)	10	20	30	40	50
추세선식	$Y = 3.906X - 0.42$				
상관계수 (r^2)	0.9992				
전달속도 V_i (Km/s)	3.906				
$V_d = 1.05V_i$	4.101				
품 질 평 가	양호				



초음파법에 의한 콘크리트 압축강도(Mpa)	
f_{ck} (일본건축학회식)	25.6
f_{ck} (일본재료학회식)	29.5

측정위치	P4-코핑				
X (전달시간, μs)	26.8	52.1	75.3	101.9	126.7
Y (측정거리, cm)	10	20	30	40	50
추세선식	$Y = 4.005X - 0.663$				
상관계수 (r^2)	0.9997				
전달속도 V_i (Km/s)	4.005				
$V_d = 1.05V_i$	4.205				
품 질 평 가	양호				



초음파법에 의한 콘크리트 압축강도(Mpa)	
f_{ck} (일본건축학회식)	27.8
f_{ck} (일본재료학회식)	30.6

