

위치	측 정 치					평균치	평균치	타격 각도	▽R1	▽R3	기준 강도	f	재령	α	f ₂₈	Mpa	추정 강도
						(R ₁)	(R ₂)	(α)	(ΔR)	(ΔR')	(R ⁰)						
S1 바닥판하면	57	55	55	57	56	54.9	54.9	90	-2.74	0	52.2	48.3	2000	0.64	30.9	27	30.8
	56	52	53	55	54												
	58	54	52	54	54							48.1			30.8		
	54	55	55	55	56												
S2 바닥판하면	56	57	56	53	56	55.6	55.6	90	-2.69	0	52.9	49.2	2000	0.64	31.5	27	31.3
	57	56	56	56	55												
	55	54	54	55	56							48.6			31.1		
	56	54	56	56	58												
S3 바닥판하면	53	52	53	56	54	54.1	54.1	90	-2.80	0	51.3	47.2	2000	0.64	30.2	27	30.3
	58	56	54	53	52												
	55	53	53	52	53							47.4			30.4		
	55	52	57	56	54												
S3 바닥판하면	54	53	54	54	55	53.8	53.8	90	-2.83	0	51.0	46.8	2000	0.64	29.9	27	30.1
	54	53	51	52	54												
	55	51	54	53	53							47.2			30.2		
	55	55	56	55	54												
A1 흉벽	48	47	48	51	48	48.0	48.0	0	0.00	0	48.0	43.0	2000	0.64	27.5	24	28.2
	48	46	46	45	47												
	47	48	49	50	51							45.0			28.8		
	47	48	47	48	50												
P1 기둥	51	52	50	50	51	50.3	50.3	0	0.00	0	50.3	45.9	2000	0.64	29.4	24	29.6
	50	48	49	50	53												
	51	53	51	51	50							46.7			29.9		
	48	48	49	51	50												
P2 기둥	52	48	53	52	54	50.7	50.7	0	0.00	0	50.7	46.4	2000	0.64	29.7	24	29.9
	50	50	48	50	48												
	50	55	51	48	50							47.0			30.1		
	52	50	51	52	50												
A2 흉벽	46	46	44	50	43	47.1	47.1	0	0.00	0	47.1	41.8	2000	0.64	26.8	24	27.6
	43	47	50	46	50												
	52	48	43	48	43							44.4			28.4		
	50	51	46	48	47												