

위치	측 정 치					평균치	평균치	타격각도	▽R1	▽R3	기준강도	f	재령	α	f_{28}	Mpa	추정강도
						(R ₁)	(R ₂)	(α)	(ΔR)	($\Delta R'$)	(R ⁰)						
S1 바닥판하면	53	50	53	53	52	52.5	52.5	90	-2.93	0	49.6	45.0	2000	0.64	28.8	27	29.2
	51	57	53	53	52												
	51	52	53	52	53							46.2			29.6		
	50	55	50	54	53												
S2 바닥판하면	53	53	54	56	54	53.7	53.7	90	-2.84	0	50.9	46.6	2000	0.64	29.9	27	30.0
	49	54	53	54	55												
	49	51	52	53	52							47.2			30.2		
	59	58	55	56	54												
S2 바닥판하면	53	52	52	52	54	53.4	53.4	90	-2.86	0	50.5	46.1	2000	0.64	29.5	27	29.8
	53	54	53	55	53												
	52	54	54	53	54							46.9			30.0		
	54	53	54	54	55												
S3 바닥판하면	52	50	51	53	53	52.3	52.3	90	-2.94	0	49.4	44.7	2000	0.64	28.6	27	29.1
	49	53	51	56	54												
	50	52	52	51	53							46.1			29.5		
	52	53	52	54	54												
A1 홍벽	49	46	46	47	46	45.5	45.5	0	0.00	0	45.5	39.8	2000	0.64	25.5	24	26.6
	44	46	44	44	45												
	44	46	45	44	43							43.2			27.7		
	47	45	47	46	46												
P1 기둥	48	47	47	46	51	46.5	46.5	0	0.00	0	46.5	41.1	2000	0.64	26.3	24	27.2
	46	46	45	46	47												
	47	50	45	46	45							43.9			28.1		
	47	45	45	45	45												
P2 기둥	51	50	40	44	48	44.9	44.9	0	0.00	0	44.9	39.0	2000	0.64	25.0	24	26.2
	47	40	41	43	45												
	42	42	44	45	46							42.8			27.4		
	42	45	51	47	45												
A2 홍벽	46	45	46	45	48	46.9	46.9	0	0.00	0	46.9	41.6	2000	0.64	26.6	24	27.5
	47	48	49	46	46												
	49	46	48	48	47							44.2			28.3		
	48	48	45	46	47												