

Schmidt Hammer Test Data

위치	측정치					평균치 [R]	타격 각도 [α]	각도 보정	습윤 보정	보정치 [ΔR]	보 반발경도 [R0]	정 계 수 [αn]	압축강도(Mpa)		평 균 압축강도 (Mpa)	설 계 기준강도 (MPa)
													재료학회	건축학회		
S6	46	47	47	47	46	46.6	90	-3.4	0	-3.4	43.2	0.64	23.6	26.1	24.9	24.0
	47	45	49	47	48											
	44	46	47	47	48											
	44	46	49	45	46											
S51	50	51	47	46	45	48.0	90	-3.3	0	-3.3	44.7	0.64	24.8	26.8	25.8	24.0
	49	44	46	49	52											
	52	44	46	46	48											
	46	51	52	45	50											
S96	47	46	45	49	43	47.2	90	-3.3	0	-3.3	43.9	0.64	24.1	26.4	25.3	24.0
	46	50	47	48	44											
	50	49	47	46	46											
	47	50	47	50	47											